



**Spartan UK Ltd**

**Declaration of Performance**

(according to Annex III of EU Regulation No. 305/2011 and ammended per EU Regulation No. 574/2014)

**DOP/2019/S355J2**

Unique identification code of the product - type:

**DOP/2019/S355J2**

Intended use or uses of the construction product, in accordance with the applicable harmonized technical specification:

**Hot - rolled steel plates from structural steels accordant to the regulations of EN10025-2,-3,-5**

Name, registered trade name or registered trade mark and contact address of the manufacturer:

**Spartan UK Ltd**  
**Ropery Road, Teams, Gateshead, Tyne and Wear, NE8 2RD, United Kingdom**  
 Tel. : +44 (0) 191 4604245  
 E-mail: gary.robinson@spartanuk.co.uk

Name and representative whose mandate covers the tasks specified in Article 12 (2):

**Not Applicable**

System or systems of assessment and verification of constancy of performance (AVCP) of the construction product as set out in Annex V to Regulation (EU) No. 305/2011:

**System 2+**

In case of the declaration of performance concerning a construction product covered by a harmonized standard:

**Hot rolled plates from structural steels with strength level S235 up to S460 according to EN 10025-1:2004**

**Notified factory production control certification body TUV NORD Systems GmbH & Co. KG No. 0045**

**Große Bahnstraße 31**  
**D-22525 Hamburg**  
**Germany**

**Certificate No: 0045-CPR-0950 dated 15/10/2020**

The performance of the product identified in points 1 and 2 is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identify above

Signed for and on behalf of the manufacturer by:

**Gary Robinson, Quality Manager**

Gateshead, 20th of October 2020

Essential Characteristic	Declared Performance		Harmonised Standard
	Nominal thickness (mm)	Values (MPa) Min	
Yield Strength	≤ 16	355	EN 10025-1 (2004)
	> 16 ≤ 40	345	
	> 40 ≤ 63	335	
	> 63 ≤ 80	325	
	> 80 ≤ 100	315	
	> 100 ≤ 150	295	
	> 150 ≤ 200	285	
Tensile Strength	≥ 3 ≤ 100	470 to 630	EN 10025-1 (2004)
	> 100 ≤ 150	450 to 600	
	> 150 ≤ 250	450 to 600	
	Nominal thickness (mm)	Values (MPa)	
Elongation	> 3 ≤ 40	20	EN 10025-1 (2004)
	> 40 ≤ 63	19	
	> 63 ≤ 100	18	
	> 100 ≤ 150	18	
	> 150 ≤ 250	17	
Impact strength for longitudinal test specimens KV at -20°C	Nominal thickness (mm)	Values (J)	EN 10025-1 (2004)
	≤ 150	min 27	
	> 150 ≤ 250	min 27	

**Chemical composition of the ladle analysis:**

C in % max. for nominal product thickness in mm	Si % max. Mn % max. P % max. S % max. N % max. Cu % max. Other % max.									
	≤ 16	> 16 ≤ 40	> 40							
S355J2	0.20	0.20	0.22	0.55	1.60	0.025	0.025	-	0.55	-

**Maximum CEV based on ladle analysis**

	Maximum CEV in % for nominal product thickness in mm			
	≤ 30	> 30 ≤ 40	> 40 ≤ 150	> 150 ≤ 250
S355J2	0.45	0.47	0.47	0.49



0045

**Spartan UK Ltd, Ropery Road, Gateshead, Tyne and Wear, NE8 2RD Great Britain**

**O6**

**0045-CPR-0950**

**DOP No: DOP/2019/S355J2**

**EN10025-1:2004**

**Hot rolled plates from structural steels of Grade S355J2 / 1.0577 according to EN10025-2:2019**

**Intended uses:**

**Building constructions or civil engineering in accordance with EN1090 when supplied with 3.1 certification to EN10204 containing product identification details.**

Information on regulated characteristics in accordance with EN10025-2 for:

**Tensile Strength:**

**Yield Strength:**

**Elongation:**

**Impact Strength:**

**Weldability:**

**Regulated substance: No performance determined**